

Properties	units	Value
Toluene solution viscosity 5,23% / 25°C	cSt	14 ± 5
Volatile matter	%m	≤ 0,8
Ash content	%m	≤ 0,3
Content of bound styrene	%m	30 ± 1,5
Standing antioxidant content	%m	≥ 0,4
Melt flow index, 200 °C/5 kg	g/10 min	< 1
Yellow index		≤ 10
Tensile strength	Mpa	15
Tensile stress at 300% elongation	Mpa	2,7
Relative elongation at break	%	700
Hardness, Shore A/ 1 sek	Units	80